

Product description

Operational sector:	Waterborne universal satin matt paint based on pure acrylate dispersion for exterior and interior use on surfaces exposed to normal stress. It is an excellent choice for high quality finishes of wooden construction elements which are out of tolerances such as roof overhang, garden houses and fences. To be also applied on primed ferrous and steel substrates, for zinc or hard PVC gutters and rain grooves, for aluminium and mineral supports such as concrete or mason, as well as firmly adhering old layers of paint based on dispersion or synthetic resins.												
Properties :	<ul style="list-style-type: none"> - Weather-resistant according to DIN 18 363, light-fast - water repellent, breathable, permanent elastic - hiding power class 1 DIN EN 13300 - wet abrasion resistance class 1 DIN EN 13300 - complies with requirements of EN 71-3 (Migration of Certain Elements) and DIN 53 160 (colour fastness to saliva and sweat) - free from fragrances and plasticiser according to 2009/48/EG (Toy Safety Directive) 												
Content as per VDL directive 01: (association of German paint industry)	Pure acrylate dispersion, titanium dioxide, water, silica based filling material, glycol, additives, preservatives												
Colour availability :	see Colour Register (Mipa Decorative Products)												
Specification :	<table border="0" style="width: 100%;"> <tr> <td style="width: 30%;">Gloss level:</td> <td style="width: 30%;">satin matt</td> <td style="width: 40%;">DIN 67 530</td> </tr> <tr> <td>Specific gravity:</td> <td>1.3 - 1.5 g/cm³</td> <td>DIN 51 757</td> </tr> <tr> <td>Viscosity:</td> <td>approx. 70 dPas</td> <td>DIN 53 019</td> </tr> <tr> <td>pH value:</td> <td>approx 8.0</td> <td>DIN 53 785</td> </tr> </table>	Gloss level:	satin matt	DIN 67 530	Specific gravity:	1.3 - 1.5 g/cm ³	DIN 51 757	Viscosity:	approx. 70 dPas	DIN 53 019	pH value:	approx 8.0	DIN 53 785
Gloss level:	satin matt	DIN 67 530											
Specific gravity:	1.3 - 1.5 g/cm ³	DIN 51 757											
Viscosity:	approx. 70 dPas	DIN 53 019											
pH value:	approx 8.0	DIN 53 785											
Storage :	At least 2 years, if the tightly closed original packages are kept dry, protected against frost. Storage temperature: from +5°C till maximum +30°C.												
VOC regulation :	EU limiting value for the product (cat. A/d): 130 g/l This product contains max. 129 g/l VOC [1.07 lbs/gal]												

Application

Processing conditions :	The object and ambient temperature should be between + 5°C and + 35°C. Do not apply if exposed to direct sunlight or high wind. Up to max. 75 % relative air humidity.
Substrate pre-treatment:	The substrate must be clean, dry, solid and free of dust, oil, grease, wax and corrosive products. Remove completely damaged and not firm old coatings Sand slightly and remove dust from firmly adhering old coatings.
Fresh timber / wooden tools :	Remove exuded resin and pitch pockets. Maximal moisture content for softwood: 15 %, for hardwood: 12 %. For exterior use, apply a first coat with Mipa WBS Holzschutzgrund Premium. Recoat with Mipa WBS Wetterschutzfarbe at the earliest after 6 hours. Adhesion according to DIN 53 151 : Gt 0

This technical data sheet is supplied for informational purposes only! According to our information, all data and recommendations correspond to the state of art and are based on years of experience in manufacturing our products. They do not exempt the user from his obligation to verify professionally, on his own responsibility, the suitability of our products to the intended purpose under prevailing conditions. Safety data sheets and warnings on packaging must be observed. We reserve the right to modify and to complete the information content at any time, without prior notice or obligation to update.

New wood:	Clean and free the surface from resin and other exuding wood components. If water-soluble components are to be expected in the wood substrate a pretreatment with Mipa WBS Isoliergrund is recommended.																
Old wood :	Sand the weathered layers down to healthy wood. Apply subsequently Mipa WBS Holzschutzgrund Premium on untreated areas. If water-soluble components are to be expected in the wood substrate an intermediate coating with Mipa WBS Isoliergrund is recommended.																
Metal :	<p>Iron, steel: For a good corrosion protection, apply a priming coat with Mipa WBS Primer or Mipa WBS Allgrund. Recoat at the earliest after 4 hours with Mipa WBS Wetterschutzfarbe. Adhesion according to DIN 53 151: Gt 0.</p> <p>Aluminium: degrease and sand slightly. Adhesion according to DIN 53 151: Gt 0.</p> <p>Zinc: Pretreat the surface with Mipa Zinkreiniger. For sanding use aluminium oxide abrasive web (e.g. Scotch-Brite) , but in no case steel wool. Adhesion according to DIN 53 151: Gt 0.</p>																
Hard PVC :	Remove the existing separating agents (in case of new plastic parts), clean and sand gently. Adhesion according to DIN 53 151: Gt 0																
Mineral substrates :	Insulate absorbent, powdery or chalking substrates with Mipa Tiefgrund LF. Apply an intermediate coat with Mipa WBS Wetterschutzfarbe thinned up to 10 % with water. Topcoat with Mipa WBS Wetterschutzfarbe undiluted.																
Application process :	<p>Stir well before use.</p> <p>Brushing and rolling: dilute up to 10 % with water in case of strong absorbent substrates or higher temperature.</p> <table border="0" style="width: 100%;"> <tr> <td style="text-align: center;">Spraying (Air):</td> <td style="text-align: center;">(Airless/Airmix):</td> </tr> <tr> <td>viscosity: 45 s 4 mm DIN</td> <td>70 dPas</td> </tr> <tr> <td>nozzle: 1.8 - 2.2 mm</td> <td>0.13 mm</td> </tr> <tr> <td>pressure: 3 - 4 bar</td> <td>180 bar</td> </tr> <tr> <td>spray passes: 2</td> <td>2</td> </tr> <tr> <td>dilution: 20 % water</td> <td>undiluted</td> </tr> <tr> <td>spraying angle: 50° (dependable on surface size)</td> <td></td> </tr> <tr> <td colspan="2">Flush off time between spray passes: 10 min.</td> </tr> </table>	Spraying (Air):	(Airless/Airmix):	viscosity: 45 s 4 mm DIN	70 dPas	nozzle: 1.8 - 2.2 mm	0.13 mm	pressure: 3 - 4 bar	180 bar	spray passes: 2	2	dilution: 20 % water	undiluted	spraying angle: 50° (dependable on surface size)		Flush off time between spray passes: 10 min.	
Spraying (Air):	(Airless/Airmix):																
viscosity: 45 s 4 mm DIN	70 dPas																
nozzle: 1.8 - 2.2 mm	0.13 mm																
pressure: 3 - 4 bar	180 bar																
spray passes: 2	2																
dilution: 20 % water	undiluted																
spraying angle: 50° (dependable on surface size)																	
Flush off time between spray passes: 10 min.																	
Thinner :	water																
Drying time :	<p>Before drying at higher temperature allow a flash-off time of 10 - 15 min. The drying time depends heavily on coat thickness, temperature and relative air humidity.</p> <table border="0" style="width: 100%;"> <tr> <td></td> <td style="text-align: center;"><u>20° C</u></td> <td style="text-align: center;"><u>60° C</u></td> </tr> <tr> <td>dust dry</td> <td style="text-align: center;">40 min.</td> <td style="text-align: center;">15 min.</td> </tr> <tr> <td>dry to touch</td> <td style="text-align: center;">1 h</td> <td style="text-align: center;">30 min.</td> </tr> <tr> <td>tack free:</td> <td style="text-align: center;">> 4 h</td> <td style="text-align: center;">1 ½ h after cooling</td> </tr> </table>		<u>20° C</u>	<u>60° C</u>	dust dry	40 min.	15 min.	dry to touch	1 h	30 min.	tack free:	> 4 h	1 ½ h after cooling				
	<u>20° C</u>	<u>60° C</u>															
dust dry	40 min.	15 min.															
dry to touch	1 h	30 min.															
tack free:	> 4 h	1 ½ h after cooling															
Spreading Rate :	approx. 7 m ² / l depending on substrate and application method																

This technical data sheet is supplied for informational purposes only! According to our information, all data and recommendations correspond to the state of art and are based on years of experience in manufacturing our products. They do not exempt the user from his obligation to verify professionally, on his own responsibility, the suitability of our products to the intended purpose under prevailing conditions. Safety data sheets and warnings on packaging must be observed. We reserve the right to modify and to complete the information content at any time, without prior notice or obligation to update.

Special Recommendations

Mipa WBS Wetterschutzfarbe is not suitable for application where blocking properties are essential. Regular and professional maintenance is essential for the serviceability and the durability of the treated wood construction elements. Stir well and strain before Airless application.

Cleaning of tools

Tools should be cleaned immediately after use with water. Spraying dust should be cleaned immediately with water. Dried films can be removed with a paint remover (Mipa Abbeizfluid).

This technical data sheet is supplied for informational purposes only! According to our information, all data and recommendations correspond to the state of art and are based on years of experience in manufacturing our products. They do not exempt the user from his obligation to verify professionally, on his own responsibility, the suitability of our products to the intended purpose under prevailing conditions. Safety data sheets and warnings on packaging must be observed. We reserve the right to modify and to complete the information content at any time, without prior notice or obligation to update.